

F-19280 AQUA FDA GLOSS WR CLEAR

PRODUCT DESCRIPTION

Designed to provide a gloss protective coating that resists grease, oil and water on uncoated or coated paper and board stock and most plastic films. When applied as a continuous film, it complies with FDA CFR 176.170 and 176.180 under conditions described in the Use section below. Product performance may be affected by choice of substrate, application equipment and environmental conditions. It is always recommended to pre-test before running production.

APPLICATIONS

- Flexo
- Rotogravure
- Litho AQ Coating Unit
- Other Coating Equipment

SUBSTRATES

- Paper
- Board
- Some Plastic Films

CHARACTERISTICS

- Ease of clean-up
- Grease, oil and water resistant
- FDA compliant for direct food contact*
- Freeze/Thaw Resistant
- High solids
- Low foaming
- Water reducible

PROPERTIES

- Flash Point: >230°F
- Coating VOC: 33 grams/liter.
- pH: 8.56
- Weight/gallon: 8.71
- Viscosity: Zahn 3=16-18 sec.
- % Solids: 48.60%

USE*

This coating, when used in contact with aqueous or fatty foods, has prior sanction and is covered under FDA Regulation 21 CFR 176.170 for use only in contact with food of types IV-A and VII under use conditions E-G in Table 2 and with food type VIII without use restriction. In contact with dry food, has prior sanction and is covered under FDA Regulation 21 CFR 176.180.

STORAGE

Protect from freezing. Store at room temperature (Below 100 F.) Reseal containers tightly.

PACKAGING

Available in 5 gallon kits, and 55 Gallon drums.

PRECAUTIONS

Read the Material Safety Data Sheet prior to processing. It contains instructions for precautions when processing, handling and storing inks, and important first aid information.

OBLIGATION OF MANUFACTURER/SELLER

The following is made in lieu of all warranties, expressed or implied: Seller's and manufacturer's only obligation shall be to replace such quantity of the product proved defective. Neither seller nor manufacturer shall be liable for any injury, loss or damage, direct, or incidental or consequential, arising out of the use of or the inability to use the product. Before using, the user shall determine the suitability of the product for his intended use and user assumes all risk and liability whatsoever in connection therewith. The foregoing may not be altered except by an agreement signed by officers of seller and manufacturer. ALWAYS PRE-TEST BEFORE RUNNING PRODUCTION.