

## F-19080 AQUA GREASE/MOISTURE BARRIER COAT

### PRODUCT DESCRIPTION

Designed to provide excellent holdout required for grease, oil, and moisture resistance on uncoated or coated paper and board stock. Resists the migration of grease, oil, water, and the sticking of food at temperatures below 225°F. Not intended to be used for release under the high temperature conditions required for the baking of food products. Excellent performance in freezer conditions.

### APPLICATIONS

- Flexo
- Rotogravure
- Litho AQ Coating Unit
- Other Coating Equipment

### SUBSTRATES

- Paper
- Board
- Some Plastics

### CHARACTERISTICS

- Good Release at temperatures <225°
- Balance of low COBB and MVTR
- Excellent grease, oil and water resistance
- Ease of clean-up
- Freeze Resistant
- Water reducible
- High solids
- Repulpable
- Recyclable
- Low foaming
- FDA compliant for direct food contact

### PROPERTIES

- Flash Point: >145°F
- Coating VOC: <10 grams/liter
- Weight/gallon: 8.70
- pH: 8.51
- Viscosity: Zahn 3=18-20 sec.
- % Solids: 42.3%

### USE

This coating, when used in contact with aqueous or fatty foods, has prior sanction and is covered under FDA Regulation 21 CFR 176.170 for use only in contact with food of types IV-A and VII under use conditions E-G in Table 2 and with food type VIII without use restriction. In contact with dry food, has prior sanction and is covered under FDA Regulation 21 CFR 176.180.

### STORAGE

Protect from freezing. Store at room temperature (Below 100 F.) Reseal containers tightly.

### PACKAGING

Available in 5 gallon kits, and 55 Gallon drums.

### PRECAUTIONS

Read the Material Safety Data Sheet prior to processing. It contains instructions for precautions when processing, handling and storing inks, and important first aid information.

#### OBLIGATION OF MANUFACTURER/SELLER

The following is made in lieu of all warranties, expressed or implied: Seller's and manufacturer's only obligation shall be to replace such quantity of the product proved defective. Neither seller nor manufacturer shall be liable for any injury, loss or damage, direct, or incidental or consequential, arising out of the use of or the inability to use the product. Before using, the user shall determine the suitability of the product for his intended use and user assumes all risk and liability whatsoever in connection therewith. The foregoing may not be altered except by an agreement signed by officers of seller and manufacturer. ALWAYS PRE-TEST BEFORE RUNNING PRODUCTION.