



SWISS BRILLIANCE IN COATING

TECHNICAL DATA SHEET

F-19292 WESSCO® 30.356.22 UV COATING HIGH GLOSS

Viscosity 50s DIN #4, 22.5s Zahn #3, 230 CPS

For coatings on digital prints

Solvent-free, UV-curable high-gloss coating for finishing paper, board and plastic film.

Not suitable for coating of food stuff and other sensitive packaging. This applies for secondary packaging too, unless a barrier avoids migration of substances to the content. Before the finished secondary packaging is brought into circulation corresponding migration tests shall be conducted.

For digital printing machinery, using flexo/roller coater application. In- and Offline application.

1. Application

- Digital Prints

2. Product Properties

- **low odor**
- liquid
- solvent-free (100% system)
- colorless
- light sensitive
- heat sensitive

3. Properties of the finished product

Even, smooth and high gloss appearance:

- **not suitable for gluing**
- **not suitable for foil stamping**
- high degree of refinement
- high scuff resistance
- high chemical resistance
- can be further processed immediately
- suitable for folding and creasing, depending upon substrate
- can be recycled with de-inking process

4. Technical Data

Solid content	100 %
Flashpoint	>100°C (212°F)
Viscosity 23°C (73.4°F)	
-DIN #4 Cup;	50 ± 5s
-Zahn #3 Cup;	22.5 ± 5s
-Centipoises;	230 CPS
Reactivity per lamp 80 W/cm	30 m/min.
(200 W/inch) reference value	(99 f/min)

5. Further Processing

Preliminary tests are imperative!

6. Coating preparations

- **Stir very well before use.**
- Check machine for cleanliness.

7. Processing

7.1 Method of Application:

- Roller application
- Chamber blade application

7.2 Speed

Must be adapted to number, power, state of UV-lamps as well as to substrate to achieve full curing of the coating.

7.3 Curing

Degree of curing may vary, depending upon substrate and state of UV-curing equipment.

7.4 Cleaning

Clean all equipment with appropriate washes after use.

7.5 Stacking behavior

Check regularly degree of curing, temperature and flatness at delivery end.

8. Packaging

Canister	25 kg (6.6 gallon, 55 lbs)
Drum	200 kg (55 gallon, 440 lbs)
Tote	1000 kg (275 gallon, 2204 lbs)

9. Safety Precautions

Refer to WESSCO® 30.356.22 Material Safety Data Sheet complying with Regulation 1907/2006/EC and observe warnings on packs.

10. Transport

Non dangerous good!

Please refer to "General technical information for WESSCO® UV coatings".

No.1 /04.12

The information contained in this publication is correct to the best of our knowledge and belief. No liability can be accepted on our part. Given the many different applications and processing methods, you should always conduct your own tests on our products before commencing production.