

# TECHNICAL DATA SHEET

# WESSCO® 36.245.15 UV-COATING EXTRA MATT

Viscosity 60s DIN #4, 27.5s Zahn #3, 280 CPS

Solvent-free, UV-curable matt coating for refinement of paper, board and plastic film.

Not suitable for coating of food stuff and other sensitive packaging. This applies for secondary packaging too, unless a barrier avoids migration of substances to the content. Before the finished secondary packaging is brought into circulation corresponding migration tests shall be conducted.

For sheet-fed press with coating unit, Flexographic unit and Rollercoater.

## 1. Application

- Packaging
- Commercial printing

# 2. Product Properties

- low odor
- liquid
- solvent-free (100% system)
- milky
- light sensitive
- heat sensitive

#### 3. Properties of the finished product

Even, smooth and matt coating:

- extra matt
- medium slip
- high degree of finishing
- high scuff resistance
- high chemical stability
- can be further processed immediately
- suitable for folding and creasing, depending upon substrate
- can be recycled with de-inking procedure

### 4. Technical Data

Solid content 100 %

Flashpoint >100°C (212°F)

Viscosity 23°C (73.4°F)

-DIN #4 Cup;  $60 \pm 5s$ -Zahn #3 Cup;  $27.5 \pm 4s$ -Centipoises; 280 CPSReactivity per lamp 80 W/cm(200 W/inch) reference value (115 f/min)

### 5. Further Processing

Preliminary tests are imperative.

- 5.1 Gluing (conditional):
  - do not print on/over gluing flaps
  - do not use water based primer on gluing flaps
  - test glue first for suitability

## 6. Coating preparations

- Stir very well before use.
- Check machine for cleanliness.

#### 7. Processing

7.1 Method of Application
Roller application
Chamber blade application

#### 7.2 Speed

Must be adapted to number, power and state of UVlamps as well as to substrate to achieve full curing of the coating.

#### 7.3 Curina

Degree of curing may vary, depending upon substrate and state of UV-curing equipment.

## 7.4 Cleaning

<u>Clean all equipment with appropriate washes after use.</u>

#### 7.5 Stacking behavior

Check regularly degree of curing, temperature and flatness at delivery end.

#### 8. Packaging

Canister 25 kg (6.6 gallon, 55.12 lb) Drum 200 kg (55 gallon, 440.93 lb)

## 9. Safety Precautions

Refer WESSCO<sup>®</sup> 36.245.15 Safety Data Sheet complying with Regulation 91/155/EEC and observe warnings on packs.

#### 10. Transport

Non dangerous good!

Please refer to "General technical information for WESSCO" UV coatings".

No.1 /04.09

The information contained in this publication is correct to the best of our knowledge and belief. No liability can be accepted on our part. Given the many different applications and processing methods, you should always conduct your own tests on our products before commencing production.